

Technical Data Sheet

Alberdingk[®] LUX 260

Characteristic

Alberdingk[®] LUX 260 is a UV cross-linkable dispersion based on an aliphatic polyester polyurethane. It remains tacky before UV cure giving excellent flow properties and very good penetration into wood pores.

Features:

Excellent chemical and stain resistance
Excellent scratch resistance
Very fast water release
Excellent wood warmth

Specification:

| | | |
|-----------|-----|-------------|
| NVW | % | 39.0 – 41.0 |
| pH value | | 7.0 – 8.0 |
| Viscosity | cps | 100 - 500 |

According to:

DIN EN ISO 3251
1.0 g weighed quantity at 105°C
DIN ISO 976
ISO 1652, Brookfield RVT
Spindle 1/rpm 20/factor 5

Further typical data*:

| | | |
|--------------------------------|----|-----------|
| MFFT | °C | approx. 0 |
| Koenig hardness before UV cure | s | 5 |
| Koenig hardness after UV cure | s | 130 |

Applications:

Furniture coatings
KCMA coatings
Parquet flooring
General plastics
Primers

Technical Data Sheet

Alberdingk[®] LUX 260

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs)
totes (2205 lbs)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.