

Technical Data Sheet

AlberdingkUSA® LUX 399

Characteristic

AlberdingkUSA® LUX 399 is a UV curable polyurethane-acrylic copolymer with high UV reactivity. It has good re-emulsifiability, good wood warmth, good adhesion to multiple substrates and good chemical resistance.

Features:

Excellent sandability Very fast water release Excellent block resistance Excellent surface hardness

Specification:

		According to:
%	44.0 - 46.0	DIN EN ISO 3251
		1.0 g weighed quantity at 105°C
	6.5 - 7.5	DIN ISO 976
cps	10 - 500	ISO 1652, Brookfield RVT
		Spindle 1/rpm 20/factor 5
		6.5 – 7.5

Further typical data*:

MFFI	°C	approx. 0
Koenig hardness before UV cure	S	5
Koenig hardness after UV cure	S	110

Applications:

KCMA coatings Furniture coatings Wood panels MDF coatings Clear plastic coatings

Latest update December 15, 2010 Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 1 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R .China | www.alberdingkchina.com



Technical Data Sheet

AlberdingkUSA® LUX 399

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs) totes (2205 lbs) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update
December 15, 2010

Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 2 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de
Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com