

Preliminary technical data sheet

ALBERDINGK® PUR-MATT 340 VP

Characteristic:

Matt, aliphatic softfeel-polyurethane dispersion.

Specification:

Solids content	%	39.0 - 41.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value		7.0 - 9.0	ISO 976
Viscosity	mPas	20 - 500	ISO 1652, Brookfield RVT Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	ca. 10	According to:
Density at 20°C	g/cm ³	1.0 - 1.1	ISO 2811-1
Solvent-free			

Film properties*:

Ultimate tensile strength	N/mm ²	ca. 16	According to: ISO 527-1
Elongation at break	%	ca. 750	ISO 527-1
E-Modulus	N/mm ²	ca. 3.0	ISO 527-1

Properties:

- matt film-surface with softfeel haptics
- very good chemical and hydrolysis resistances
- high optical transparency on dark substrates
- OVP` s based on PUR-MATT 340 VP enhance the colour of the print underneath
- flexible film with very high coefficient of friction (antislip properties)
- suitable for 1pack and 2pack applications

Applications:

Inherent matt polyurethane dispersion which can be used as coating for e.g. plastics (also on corona treated BOPP) or in OPV's.

Preliminary technical data sheet

ALBERDINGK® PUR-MATT 340 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Further information:

Before using please stir the product well.

Notice:

* General information - the values can not be considered as part of the product specification.