

Preliminary technical data sheet

ALBERDINGK® U 228 VP

Characteristic:

Soft, solvent free, aliphatic polyether-polyurethane dispersion.

Specification:

Solids content	%	59.0 - 61.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value		7.5 - 9.5	ISO 976
Viscosity	mPas	200 - 1000	ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20

Further typical data*:

MFFT	°C	ca. 0	According to:
Density	g/cm ³	1.0 - 1.1	ISO 2811-1
Solvent-free			

Applications:

For flat-roof coatings, or also for soft and flexible coating systems on e.g. leather, textile and plastics.

Preliminary technical data sheet

ALBERDINGK® U 228 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Further information:

The product tends to form sedimentation, so it has to be stirred very well before use.

Notice:

* General information - the values can not be considered as part of the product specification.