

Product Information

Alberdingk[®] U 3251

What is the resin's nature?

Highly flexible, solvent-free, aliphatic polyester polyurethane dispersion.

Technical data:

Solids content:	39 - 41%
pH-value:	7.0 - 8.0
Viscosity:	20 - 200 mPas
MFFT:	approx. 0 °C
elongation at break:	approx. 650%

Why has the resin been developed?

- high elasticity
- blocking resistance
- plasticizer properties for hard acrylics

What is the suggested field of application?

- Textile / leather coatings
- For exterior applications
- For parquet varnishes (as co-binder < 20%)

Product Information

Alberdingk[®] U 3251

Suitable raw materials

Defoamers:

Byk 024 (BYK Chemie)

Tego Foamex 822 (Evonik Tego Chemie)

Substrate wetting agents:

Byk 346 (BYK Chemie)

Dow Corning 67 (Dow Corning)

Coalescing agents:

Dowanol DPM (Dow Chemical)

Butylcellosolve, BG (BASF)

Dowanol DPnB (Dow Chemical)

Matting agents:

Acematt TS 100 (Evonik)

Rheology control additives:

DSX 1514 (BASF)

DSX 2000 (BASF)

Tego Viscoplus 3000 (Evonik Tego Chemie)

Product Information

Alberdingk[®] U 3251

Formulation Proposal

FP 3251-1 plastic coatings

Pos.	Raw Materials	Amount	Supplier
1	ALBERDINGK[®] U 3251	80.00	Alberdingk Boley
2	Dow Corning 67	0.50	Dow Corning
3	Byk 024	1.00	BYK Chemie
4	Butylcellosolve (BG)	5.00	BASF
5	Water (deion.)	12.20	
6	Acematt TS 100	1.00	Evonik
7	DSX 1514	0.30	BASF
Total		100.00	

premix pos. 4 + 5 before use

Please take note of local regulations, that might limit or ban the use of raw materials such as 2-(2-Butoxyethoxy)ethanol [=BDG; = Butylcarbitol] or 2-Butoxyethanol [= BG; = Butylcellosolve].

Example: Decision No. 1348/2008/EG

Latest update
Jan 01, 2011

Alberdingk Boley GmbH | Düsseldorf Str. 53 | 47829 Krefeld | Germany
Phone +49 2151 528-0 | Fax+49 2151 573643 | info@alberdingk-boley.de | www.alberdingk-boley.de

page 3 of 3

Alberdingk Boley, Inc. | Greensboro, NC | USA | www.alberdingkusa.com
Alberdingk Resins (Shenzhen) Co., Ltd. | Shenzhen | P. R. China | www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or a suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.