

Technical Data Sheet

AlberdingkUSA® U 9270

Characteristic

AlberdingkUSA® U 9270 is a NMP-free, self-crosslinking, aliphatic polyester polyurethane dispersion that can be formulated for high-performance wood coatings. It has excellent film hardness and chemical/stain resistance.

Features:

Suitable for one-component wood floor finishes (MFMA compliant!)
Excellent black heel mark resistance
High gloss
Outstanding blocking resistance
Excellent abrasion resistance

Tentative Specification:

NVW	%	40.0 – 42.0
pH value		8.0 – 9.0
Viscosity	cps	30 - 500

According to:

DIN EN ISO 3251
1.0 g weighed quantity at
105°C
DIN ISO 976
ISO 1652, Brookfield RVT
Spindle 1/rpm 20/factor 5

Further typical data*:

Density, lbs/gal (g/cm ³)	8.76 (1.05)
VOC, g/L	31
MFFT (°C)	46
Koenig hardness, s	142

Applications:

Sports flooring (1K & 2K)
Parquet flooring
High gloss enamels
Wood coatings

Technical Data Sheet

AlberdingkUSA® U 9270

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs)
totes (2205 lbs)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.