

Technical data sheet

ALBERDINGK® U 9900

Characteristic:

Aqueous, anionic, solvent-free dispersion of an aliphatic polyester-polyurethane.

Specification:

Solids content	%	39.0 - 41.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value		7.5 - 9.0	ISO 976
Viscosity	mPas	20 - 200	ISO 2555, Brookfield RVT Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	ca. 50	According to:
Density	g/cm ³	ca. 1.06	ISO 2811-1
Solvent-free			

Film properties*:

Pendulum hardness (König)	s	ca. 160	According to: ISO 1522
---------------------------	---	---------	----------------------------------

Applications:

High-quality single and two-pack wood coatings. Exhibits very high chemical and stain resistance, excellent clarity on wood as well as very high film hardness. Suitable for clear and pigmented applications.

Technical data sheet

ALBERDINGK® U 9900

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.