

Technical Data Sheet

AlberdingkUSA® AC 2514

Characteristic

AlberdingkUSA® AC 2514 is a medium hard self crosslinking acrylic dispersion. It is suitable for a wide variety of applications.

Features:

Excellent Surface Hardness
High Gloss
Quick Drying

Excellent Chemical Resistance including Hand Lotion

Specification:			According to:
NVW	%	42.0 - 44.0	DIN EN ISO 3251
			1.0 g weighed quantity at 105°C
pH value		7 - 8	DIN ISO 976
Viscosity	cps	30 - 300	ISO 1652, Brookfield RVT
			Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	approx. 45
Tg	°C	approx. 52
Koenig hardness	S	approx. 110

Applications:

Wood Primers Sanding Sealers KCMA Furniture

Concrete

Latest update June 11, 2010 Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 1 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de
Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



Technical Data Sheet

AlberdingkUSA® AC 2514

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs) totes (2205 lbs) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update June 11, 2010 Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 2 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de
Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com