

Preliminary technical data sheet

ALBERDINGK® AC 2765 VP

Characteristic:

Aqueous, fine disperse copolymer dispersion of an acrylic acid esters.

Specification:

Solids content	%	44.0 - 46.0	According to: ISO 3251 1.0 g weighed quantity at 105°C
pH- value		8.0 - 9.0	ISO 976
Viscosity	mPas	10 - 300	ISO 2555, Brookfield RVT Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	ca. 65	According to:
Density	g/cm ³	1.0 - 1.1	ISO 2811-1
Solvent-free			

Applications:

For pigmented coatings with excellent chemical resistance against ethanol & coffee.

In combination with the right primer (e.g. based on ALBERDINGK® AC 2742) suitable for IKEA R2 & R0 systems.

As clear coat on wood it shows a solvent borne- or NC-like excellent wood warming.

Preliminary technical data sheet

ALBERDINGK® AC 2765 VP

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.