

Preliminary technical data sheet

ALBODUR® 102 VP

Characteristic:

OH-functional polyol based on castor oil (renewable raw materials).

Specification:

			According to:
Acid value	mg KOH/g	1.00 - 3.00	ISO 660
Water content	%	0.00 - 0.10	ISO 8534
Iodine colour value		2.0 - 5.0	DIN 6271
Gardner colour value		2.0 - 5.0	ISO 4630
Hydroxyl value	mg KOH/g	80 - 100	ISO 4629-2
Viscosity acc. to Brookfield cone plate at 25°C, cone 5, 500upm	mPas	500 - 700	ISO 2884

Further typical data*:

			According to:
Non-volatile compounds	%	ca. 100	
Solvent-free			
Density at 23°C	g/cm ³	0.97 - 0.98	ISO 2811-3
Functionality (cal.)		2.0	
Shore A hardness		ca. 55	DIN 53505

Applications:

Polyol with hydrophobing properties for polyurethane systems, e.g. adhesives, coatings, casting resins, sealants and foams. Compatible with most polyether and/ or polyester polyols and can be blended with other diols or triols to achieve preferable modifications of product properties.

Preliminary technical data sheet

ALBODUR® 102 VP

Storage:

In originally closed containers, ALBODUR® polyols and oil polymers are stable for 6 months when stored at recommended temperature range from +5°C to +30°C. The products should be protected from atmospheric oxygen.

A turbidity of the products due to coldness is reversible and can be removed by heating up to more than 40 °C.

ALBERDINGK BOLEY GmbH assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH.

Packaging:

steel drums (190 kg)
one-way container (approx. 900 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values cannot be considered as part of the product specification.

The measurement of the shore hardness is performed by the following formulation:

94.5% ALBODUR® + 5.0% ALBOLITH MS C 350 + 0.5% BYK-088 (BYK chemistry).

Crosslinked with Suprasec 2496 (Huntsman). Crosslinking ratio 110%.

The results are measured after curing 7 days at RT.