

# Preliminary technical data sheet

## ALBODUR® 904 VP

### Characteristic:

OH-functional polyol component, based on castor oil (renewable raw materials).

### Specification:

Solids content	%	ca. 100	<b>According to:</b> DIN EN ISO 3251
Acid value	mgKOH/g	ca. 3	DIN EN ISO 2114
Gardner colour value		ca. 5	DIN EN 1557
Viscosity acc. to Höppler	mPas	ca. 700	DIN 53015 at 25°C

### Further typical data\*:

Hydroxyl value	mgKOH/g	ca. 214	<b>According to:</b> DIN 53240
OH-content as supplied	%	ca. 6.48	
OH-equivalent weight		ca. 262	
Solvent-free			

### Applications:

If crosslinked with e.g. an aromatic polyisocyanate, flexible coatings at low temperature are obtained.

### Storage:

In originally closed containers ALBERDINGK-polyols and oilpolymers are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 10 - 30°C.

The products should be protected from atmospheric oxygen.

ALBERDINGK BOLEY GmbH assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH.

# Preliminary technical data sheet

## ALBODUR® 904 VP

**Packaging:**

steel drums (190 kg)  
one-way container (approx. 900 kg)  
as bulk in tank cars, by agreement.

**Safety:**

For further information on product safety please refer to the actual material safety data sheet.

**Notice:**

\* General information - the values can not be considered as part of the product specification.