

# Technical data sheet

## ALBERDINGK® AS 2040

### Characteristic:

APEO- & ammonia-free styrene acrylic dispersion.

### Specification:

Solids content	%	56.0 - 58.0
pH- value		7.0 - 9.0
Viscosity	mPas	1500 - 4500

### According to:

ISO 3251  
1.0 g weighed quantity at  
105°C  
  
ISO 976  
ISO 2555, Brookfield RVT  
Spindle 3/rpm 20/factor 50

### Further typical data\*:

MFFT	°C	ca. 0
Density	g/cm <sup>3</sup>	1.0 - 1.1
Glass transition temperature	°C	ca. - 8
Solvent-free		

### According to:

ISO 2811-1  
DSC, heating rate 20 K/min

### Applications:

For flexible sealants and screeds. Very good cement- & bitumen- compatibility.

# Technical data sheet

## ALBERDINGK® AS 2040

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.