

Technical Data Sheet

AlberdingkUSA® AS 2688

Characteristic

AlberdingkUSA® AS 2688 is an aqueous copolymer dispersion free of plasticizers and protective colloids.

Specification:

NVW % 43.0 - 45.0

43.0 - 45.0 DIN EN ISO 3251

pH value 7.5 – 8.5

cps 500 - 3000

According to:

1.0 g weighed quantity at 105°C

DIN ISO 976

ISO 1652, Brookfield RVT Spindle 3/rpm 20/factor 5

Further typical data*:

MFFT °C approx. 40
Density lbs/gal approx. 8.66

Solvent-free

Viscosity

Applications:

For use in wood, metal and plastic coatings alone or in combination with polyurethane dispersions. For primers on wood with very good appearance, high gloss and good blocking resistance.

Latest update November 30, 2010 Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 1 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de
Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com



Technical Data Sheet

AlberdingkUSA® AS 2688

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs) totes (2205 lbs) as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Latest update November 30, 2010 Alberdingk Boley, Inc. | 6008 High Point Road | Greensboro NC 27407 | Phone +1-336/454-5000 Fax +1-866/220-4750 | info@alberdingkusa.com | www. alberdingkusa.com

page 2 of 2

Alberdingk Boley GmbH | Krefeld, Germany| www.alberdingk-boley.de
Alberdingk Resins (Shenzhen) Co. Ltd. | Shenzhen City, P.R. China | www.alberdingkchina.com