

# Technical Data Sheet

## ALBERDINGK® LUX 739

### Characteristic:

Alberdingk® LUX 739 is a cost effective, UV resin for clear coatings for wood with excellent chemical and scratch resistance.

### Specification:

Solids content	%	41.0 - 43.0
pH- value		6.5 - 7.5
Viscosity	mPas	20 - 200
Spindle 1/rpm 50/factor 2		

### According to:

ISO 3251  
0.5 g weighed quantity at 105°C  
ISO 976  
ISO 1652, Brookfield RVT

### Further typical data\*:

MFFT	°C	ca. 0
Koenig hardness before UV cure	s	18
Koenig hardness after UV cure	s	122

### Applications:

Wood coatings (clear)

# Technical Data Sheet

## ALBERDINGK® LUX 739

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### Packaging:

plastic drums (120 kg)  
one-way container (approx. 1000 kg)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the actual material safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.