

Technical Data Sheet

AlberdingkUSA® M 2955

Characteristic

AlberdingkUSA® M 2955 is an epoxy - acrylic hybrid emulsion with a very high surface hardness making it an ideal blending resin to impart high performance properties. It has good adhesion to metal and concrete and can provide a wet-look on concrete or brick substrates.

Features:

High Tg – ideal for blending
Excellent Chemical Resistance to Automotive Fluids
Excellent Hot Tire Resistance
Excellent Penetration into Porous Substrates

Specification:

NVW	%	46.5 – 48.5
pH value		8.5 – 9.4
Viscosity	cps	< 500

According to:

DIN EN ISO 3251
1.0 g weighed quantity at 105°C
DIN ISO 976
ISO 1652, Brookfield RVT
Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	approx. 54
Tg	°C	approx. 59

Applications:

Concrete
Metal

Technical Data Sheet

AlberdingkUSA[®] M 2955

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs)
totes (2205 lbs)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.