

## **Technical Data Sheet**

### ALBERDINGK® PUR-MATT 910

### **Characteristic:**

Hard, matt, aliphatic polyurethane dispersion

Specification: Solids content	%	34.0 - 36.0	According to: ISO 3251 0.5 g weighed quantity at 105°C
pH- value Viscosity	mPas	7.0 - 9.0 20 - 2000	ISO 8534 ISO 2555, Brookfield RVT Spindle 2/rpm 20/factor 20
Further typical data*:		20	According to:
Further typical data*: MFFT Density at 20°C Solvent-free	°C g/cm3	ca. 30 1.0 - 1.1	According to: ISO 2811-1
MFFT Density at 20°C	-		-
MFFT Density at 20°C Solvent-free	-		ISO 2811-1

### **Applications:**

Inherent matt polyurethane dispersion which can be used as coating for e.g. wood, plastics or in OPV's.

### **Properties:**

- matt film surface
- high optical transparency on dark substrates
- hard but flexible film
- very high coefficient of friction (antislip properties)
- excellent sandability
- very good chemical resistance
- very good blocking resistance

Latest update	Alberdingk Boley GmbH   Düsseldorfer Str. 53   47829 Krefeld   Germany
11.04.2020	Phone +49 2151 528-0   Fax +49 2151 573643   info@alberdingk-boley.de   www.alberdingk-boley.de
Page 1 of 2	Alberdingk Boley, Inc.   Greensboro, NC, USA   www.alberdingkusa.com Alberdingk Resins (Shenzhen) Co.Ltd.   Shenzhen City, P.R. China   www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.

# ALBERDINGK BOLEY

# **Technical Data Sheet**

### ALBERDINGK® PUR-MATT 910

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

### **Packaging:**

plastic drums (120 kg) one-way container (approx. 1000 kg) as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the current safety data sheet.

### **Further information:**

The product tends to form sedimentation, so it has to be stirred very well before use.

### Notice:

\* General information - the values can not be considered as part of the product specification.

Latest update	Alberdingk Boley GmbH   Düsseldorfer Str. 53   47829 Krefeld   Germany
11.04.2020	Phone +49 2151 528-0   Fax +49 2151 573643   info@alberdingk-boley.de   www.alberdingk-boley.de
Page 2 of 2	Alberdingk Boley, Inc.   Greensboro, NC, USA   www.alberdingkusa.com
	Alberdingk Resins (Shenzhen) Co.Ltd.   Shenzhen City, P.R. China   www.alberdingkchina.com

The details contained herein are based on our present state of technology and shall inform on our products and their application possibilities. A lawful binding assurance of certain attributes or the suitability for a concrete operation purpose cannot be derived from this information. Industrial property rights are to be considered if required.