

Technical Data Sheet

AlberdingkUSA[®] U 910

Characteristic

AlberdingkUSA[®] U 910 is a self-crosslinking, aliphatic polyester polyurethane dispersion that can be formulated for high-performance coatings for wood and plastic. It has excellent hardness and black heel mark resistance.

Features:

Excellent chemical and plasticizer resistance
High gloss
Excellent adhesion to multiple substrates
Excellent fingernail mar resistance

Specification:

NVW	%	29.0 – 31.0
pH value		7.5 – 8.5
Viscosity	cps	30 - 100

According to:

DIN EN ISO 3251
1.0 g weighed quantity at 105°C
DIN ISO 976
ISO 1652, Brookfield RVT
Spindle 1/rpm 20/factor 5

Further typical data*:

Solvent	%	11.9
Koenig hardness	s	155
Elongation at break	%	60

Applications:

Sports flooring (1K & 2K)
Parquet flooring
High gloss enamels
Wood furniture
Plastic coatings

Technical Data Sheet

AlberdingkUSA[®] U 910

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

Packaging:

drums (460 lbs)
totes (2205 lbs)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the actual material safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.