

Technical data sheet

ALBERDINGK® U 9800

Characteristic:

ALBERDINGK® U 9800 is an aqueous, anionic, solvent-free, colloidal, low viscous dispersion of an aliphatic polyester- polyurethane without free isocyanate groups.

Specification:

Solids content	%	34.0 - 36.0	According to: ISO 3251 0.5 g weighed quantity at 150°C
pH- value		7.5 - 9.0	ISO 976
Viscosity	mPas	20 - 300	ISO 2555, Brookfield RVT Spindle 1/rpm 20/factor 5

Further typical data*:

MFFT	°C	ca. 40	According to:
Density	g/cm ³	1.0 - 1.1	ISO 2811-1
Solvent-free			

Film properties*:

Pendulum hardness (König)	s	ca. 100	According to: ISO 1522
Elongation at break	%	ca. 260	ISO 527-1

Applications:

Coating systems with superior chemical resistance and hardness. Applications: plastic, wood and metal coatings. Good compatibility with acrylic dispersions. ALBERDINGK® U 9800 is also suitable for two component coatings.

Technical data sheet

ALBERDINGK® U 9800

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.